

GENERAL DESCRIPTION

WrapPro Color PPF is a patent-pending, high-performance, self-adhesive, color coated aliphatic polyurethane film designed to protect automotive paint, and other surfaces, from harmful effects of stone chips and abrasion. It has exceptional elongation properties for ease of application and this feature allows for single piece installations. **WrapPro Color PPF** is a very low surface energy film designed to resist staining and offers superior environmental resistance and gloss retention. The clear coat employs special elastomeric polymers that allow scratches in the surface to "heal" over time, eliminating the need for frequent polishing to maintain a just-installed appearance.

WrapPro Color PPF is coated with ultra-clear, high-performance acrylic adhesive which has excellent adhesion on a broad range of surfaces, while resisting disturbances during installation.

TYPICAL APPLICATIONS

Clear & Color gloss polyurethane for stone chip protection, high wear, and abrasion. Automotive, motorcycle, RV, powersports, bicycle, aircraft and most modes of transportation.

SHELF LIFE

WrapPro recommends **WrapPro Color PPF** be stored at 50°F-90°F, and 40%-60% RH. Film should be used within 2 years of purchase.

INSTALLATION

WrapPro Color PPF is designed to be used on any fully cured OEM paint surface. Surfaces that have been repainted are only suitable for installation of the film if the surface was repainted according to recommendations as set by the OEM. WrapPro maintains a complete set of detailed installation instructions, which may be viewed at www.wrappro.com.hk. Generally, a wet application of the product is recommended.


WARRANTY

WrapPro warrants **WrapPro Color PPF** to be free of any manufacturing or workmanship defects for five (5) years from the date of purchase. The warranty does not cover damage to **WrapPro Color PPF** caused by erroneous application, accidents, or collisions, intentional misuse or ordinary wear, nor damage, dents or chips to the protected surface or film caused by impact of rocks or any other debris. WrapPro will replace any film that does not meet this warranty. The replacement of damaged film is the exclusive remedy; liability does not extend to any other damages, incidental, consequential, or otherwise.

NOTICE

The representations of performance and suitability for use contained in this Technical Data Sheet are meant only as a guide. Since only the user is aware of the specific conditions in which the product is to be used, it is the user's responsibility to determine whether the product is suitable for that intended use.

FILM CONSTRUCTION



PRODUCT SPECIFICATION

PROPERTIES	TYPICAL VALUES	TESTING CONDITIONS	STANDARDS USED
90° Peel Adhesion	> 4.0 N/cm > 5.0 N/cm	20M post-installation @ room temp 72H post-installation @ room temp	ASTM D3330, Method F ASTM D3330, Method F
Gloss	>100 GU	60° Gloss Angle	XQT 104
Aging Tests Heat Aging Xenon-arc Accelerated Weatherometer Exposure	AE< 2 E< 2, >80% Gloss Retentio	250h@80°C 4500 kJ (3461 hours)	XCON008 SAE J2527
Mechanical Ultimate Strength @ Break Tensile Elongation @ Break Shrinkage	>18 MPa >300% >1%	Test rate: 20 in/min Test rate: 20 in/min % Change in length after aging@120+2°C	ASTM D882 ASTM D882 XQT 111
Stain/Chemical Resistance Anti-freeze Unleaded Fuel Engine Oil Transmission Fluid Glass Cleaner Windshield Washer Solvent	No Detrimental Effect No Detrimental Effect No Detrimental Effect No Detrimental Effect No Detrimental Effect No Detrimental Effect	24 hour immersion 24 hour immersion 24 hour immersion 24 hour immersion 24 hour immersion 24 hour immersio	XQT 251 XQT 257 XQT 253 XQT 262 XQT 255 XQT 256

RECOMMENDED SHELF LIFE - 2 years from date of purchase*

*if installing film after recommended shelf-life, re-certification by WrapPro is required.

RECOMMENDED STORAGE CONDITIONS

72° F (22°C) @ 50% RH



WhatsApp

Wrappro Limited

Flat B, G/F, On Ho Industrial Building, 17-19 Shing Wan Road, Tai Wai, Shatin, N.T., Hong Kong

INTERNATIONAL : +852 2387 6638

FAX : +852 3585 0059

www.wrappro.com.hk

© 2024 WrapPro Limited